

We were mentioned in the *New York Times*! An article about oil change frequency ("[The 3,000-Mile Oil Change is Pretty Much History](#)") was picked up by Yahoo News and Google News and spurred additional coverage by NPR, CBC, and others.

## ZDDWhat?

By Ryan Stark

Any search on the Internet today with regard to oil additives will eventually bring up the supposed problem that there is a lack of anti-wear additive called zinc dialkyl-dithiophosphate (shortened to ZDDP and showing up as the elements zinc and phosphorus ) in the new oils. People are worried the lack of ZDDP is causing the destruction of many older flat-tappet engines.

This first part of the problem seems to stem from an EPA mandate that all oil companies either reduce or eliminate ZDDP from their oils. While I'm sure the EPA mandates a lot of things, if they are telling the oil companies to get rid of this additive in their oils, the oil companies don't appear to be listening. Any automotive engine oil sample you send will have both zinc and phosphorus in it and at fairly high levels (anywhere from 500 to 1,000 ppm and often times a lot more). So the first part of this issue isn't really an issue at all, and that brings up the second part of the issue.

Is a lack of ZDDP really a problem for flat-tappet engines? My first inclination would be to say no, and that's because 99% of all piston aircraft engines don't use that additive in their oil. Most aircraft engines are air-cooled, so they tend to run hot and due to this, they require the use of an ashless oil. That simply means that when the oil burns, it must burn completely and not leave any ash behind. Aircraft engines are mostly flat-tappet engines and they seem to get along just fine without ZDDP. So is the second part of the problem really a problem?

I'm a mechanical engineer by training, and when I was in school, we learned the best way to answer that would be to follow the scientific method.

### The Scientific Method

If you made it this far, then I guess you weren't tired when you started reading this because the mere mention of the scientific method has been known to cause many a high school and college kid to nod off almost immediately. For those who don't remember what that method is, here's quick refresher. But wait, before you continue reading, go get a cup of coffee because I don't want to lose any of you.

1. Define the question
2. Gather information and resources (observe)
3. Form hypothesis
4. Perform experiment and collect data
5. Analyze data
6. Interpret data and draw conclusions that serve as a starting point for new hypothesis
7. Publish results
8. Retest (frequently done by other scientists)

### 1. Define the question: Is the lack of ZDDP a problem?

Apparently, the lack of ZDDP in the oil is causing the demise of older engines that still use flat tappets because without that anti-wear additive present, the camshaft lobes and tappets grind down to nothing,

especially when the engine is brand new. The thing is, this doesn't necessarily happen to all of the camshaft lobes, just a select few. The magazine Popular Mechanics recently did an article on this and they showed a picture of a camshaft with one lobe worn down to nothing. I have my doubts about this because if there really was a problem with the oil, wouldn't it affect all of the camshaft lobes and not just one? I don't pretend to know all there is to know about camshaft design and surface hardness, but I know enough to reason that all of the lobes and tappets are lubricated by oil, and if the oil was indeed substandard, then wouldn't it affect all of the lobes the same way?

This brings us to our next point: What would happen if you ran an oil that didn't have any ZDDP in it at all? If that additive is so important, wouldn't the complete lack of it cause camshafts to self destruct in a short period of time? I don't think so, because aircraft engines do it all the time and the good majority of those last to 2,000 hours and well beyond.

ELEMENTS IN PARTS PER MILLION	MI/HR on Oil		UNIT / LOCATION AVERAGES
	MI/HR on Unit		
	Sample Date	02/16/08	
	Make Up Oil Added		
ALUMINUM	0	0	
CHROMIUM	0	0	
IRON	0	0	
COPPER	0	0	
LEAD	0	0	
TIN	0	0	
MOLYBDENUM	0	41	
NICKEL	0	0	
MANGANESE	0	0	
SILVER	0	0	
TITANIUM	0	0	
POTASSIUM	0	0	
BORON	0	70	
SILICON	2	3	
SODIUM	0	1	
CALCIUM	0	975	
MAGNESIUM	1	5	
PHOSPHORUS	0	392	
ZINC	0	423	
BARIIUM	0	0	

Figure 1: Aeroshell W65

### 2. Gather information and resources (observe)

Not much to do here. I did have to order some oil that didn't contain ZDDP. That was Aeroshell W65 (see Figure 1, left). It's a 30W oil commonly used by aircraft engines during colder months. That viscosity is close to the 10W/30 (at 210°F) that I normally run. It's important to note that while this oil doesn't contain any additives that we read, it is known as an ashless dispersant oil, so there are some additives in there.

### 3. Form hypothesis: The lack of ZDDP isn't a problem at all

Never did understand this part. Isn't it the same as define the question? Maybe I was asleep at the time. In any case, here goes. I don't think the lack of ZDDP is a problem at all, based on all of the normal looking aircraft engines we analyze that do not run that additive.

### 4. Perform experiment and collect data: My own engine

Since this is my experiment, I decided to use my own engine at a guinea pig. Back in 2004 I rebuilt the GM 350 engine in my 1984 Chevy ¾ ton pick-up truck. The rebuilding process didn't quite go as planned (see our [July 2010 newsletter](#)) but the engine has been running well since then and since it has flat tappets, I thought it would be a good engine to test. I control the operating conditions and another plus is that if the engine decides to explode, I'm the only one to blame and I won't sue myself for damages, though there may be some lawyers who would take that case.

I changed oil originally back in February of 2008. Here is the report on the oil that I took out (see Figure 2 on the next page). Not the best data, especially at lead, from bearings, but at least it's consistent.

ELEMENTS IN PARTS PER MILLION	MI/HR on Oil	1,469	UNIT / LOCATION AVERAGES
	MI/HR on Unit	182,949	
	Sample Date	02/16/08	
	Make Up Oil Added	0 qts	
ALUMINUM	3	4	
CHROMIUM	3	2	
IRON	25	31	
COPPER	3	6	
LEAD	24	20	
TIN	5	3	
MOLYBDENUM	260	92	
NICKEL	0	0	
MANGANESE	9	3	
SILVER	0	0	
TITANIUM	0	0	
POTASSIUM	1	0	
BORON	32	19	
SILICON	16	12	
SODIUM	6	9	
CALCIUM	1841	1205	
MAGNESIUM	31	115	
PHOSPHORUS	685	562	
ZINC	868	665	
BARIUM	0	0	

Figure 2: The original oil was Havoline 10W/30

fill and it turns out for this engine, about 20% of the old oil remains in the engine after an oil change. This is important to note because 20% of the metals are leftover from the last oil fill as well. But the data from one sample doesn't make for good science and I still had more Aeroshell to use, so I ran it again. This would help make sure the data was consistent and also make sure the lingering additives from the regular engine oil weren't affecting my results.

The second oil was changed on October 30, 2010, after another 16 months and 1,921 miles this time (see the Report of the Month on page 5). At first glance you will notice a nice improvement in wear, especially lead. Does this mean the Aeroshell W65 is actually working better than other oils? Alas, no. What you don't see in the data is that I took a 675-mile road trip during this oil run and I strongly suspect that highway trip is the reason for the improved wear, rather than any miraculous improvement due to Aeroshell.

This is an important fact to think about whenever you are looking at someone else's oil report. Driving conditions can have a large effect on the data and unless you know what those conditions are, it is very easy to draw the wrong conclusions. The conclusion I can draw is that no, my engine did not self-destruct running this oil. I didn't actually visually inspect the camshaft, before or after this test, so I don't know how much, if any, actual wear occurred in that area. So the test isn't perfect in that regard, but I can say the engine is still running just fine.

## 5. Analyze data

That was the easy part. I've been looking at oil reports every afternoon since 1997, and I don't have to pay for the samples.

## 6. Interpret data and draw conclusions that serve as a starting point for a new hypothesis

After 16 months and 1,943 miles I decided it was time to change the oil. You can see the results in Figure 3, below. At first glance it would seem that the engine's steel parts didn't really agree with the new oil. Iron went up to 37 ppm, which isn't really a problem level, but more than I had been seeing. However, it's also important to note that this was the longest I had run the oil since the rebuild, both in time and mileage. Also, the engine doesn't have any emission controls (don't tell the EPA) and had an open breather coming off one of the valve covers. So with it being exposed to the atmosphere, there is always a chance for rust to form on the parts, and that could account for the increase in iron. Lead was still excessive, but that didn't really change, and nothing else unusual was present.

Note that this oil still had some additive in it (molybdenum, calcium, phosphorus, and zinc). These are leftover from the last

ELEMENTS IN PARTS PER MILLION	MI/HR on Oil	1,943	UNIT / LOCATION AVERAGES
	MI/HR on Unit	184,892	
	Sample Date	06/20/09	
	Make Up Oil Added	0	
ALUMINUM	5	4	
CHROMIUM	3	2	
IRON	37	31	
COPPER	3	6	
LEAD	29	20	
TIN	7	3	
MOLYBDENUM	59	92	
NICKEL	0	0	
MANGANESE	5	3	
SILVER	0	0	
TITANIUM	0	0	
POTASSIUM	0	0	
BORON	5	19	
SILICON	14	12	
SODIUM	7	9	
CALCIUM	424	1205	
MAGNESIUM	7	115	
PHOSPHORUS	152	562	
ZINC	214	665	
BARIUM	0	0	

Figure 3: The first run on Aeroshell W65

So do we have a starting point for a new hypothesis now? Yes. Would my engine be okay if I had used this oil during break-in? Maybe, but we'll won't know until I rebuild another engine. When I do, I plan on use another oil that's popular in the aircraft community: straight mineral oil with no additive whatsoever. Probably about 80% to 90% of the aircraft engines are broken in on this type of oil and they seem to do fine. Are there any other new hypotheses? I'm sure there will be many that come by and most of them will center on how this test is invalid for some reason or another. And in response to that I would refer to section 8 of the scientific method.

### **7. Publish results: That's what you are reading**

Not much to talk about here, and that brings us to our last point on the scientific method.

### **8. Retest (frequently done by other scientists)**

In this case, the other scientists are you and while I'm not suggesting any of you run Aeroshell in your automotive engines, you can use oil analysis to help solve questions you may have. Is synthetic oil really better than petroleum oil? Is that additive you're using really helping? Feel free to draw up your own hypothesis and run your own tests. Don't just buy an oil or additive, start using it, and then never stop just because the engine is running just fine. Be objective and do some testing. I think you'll be surprised by the results.

# Report of the Month

This is Ryan's 84 Chevy. It's running oil that contains no ZDDP at all. What do you think about wear?

To learn where the various elements are coming from, [click here](#).

ELEMENTS IN PARTS PER MILLION	MI/HR on Oil	1,921	UNIT/ LOCATION AVERAGES	1,943	1,469	1,682	1,603	UNIVERSAL AVERAGES
	MI/HR on Unit	186,813		184,892	182,949	181,480	179,802	
	Sample Date	10/30/10		06/20/2009	02/16/2008	06/24/2007	05/04/2006	
ALUMINUM	5	4	5	3	4	3	7	
CHROME	2	2	3	3	2	2	2	
IRON	33	31	37	25	26	18	36	
COPPER	2	6	3	3	4	2	11	
LEAD	15	20	29	24	34	19	13	
TIN	0	3	5	5	9	2	2	
MOLYBDENUM	21	92	59	260	147	167	51	
NICKEL	0	0	0	0	0	0	1	
POTASSIUM	1	0	0	1	1	0	5	
BORON	2	19	5	32	25	23	42	
SILICON	18	12	14	16	24	19	23	
SODIUM	5	9	7	6	5	3	30	
CALCIUM	84	1205	424	1841	1722	1411	1965	
MAGNESIUM	4	115	7	31	11	6	236	
PHOSPHORUS	31	562	152	685	695	607	784	
ZINC	46	665	214	868	712	712	949	
BARIUM	0	0	0	0	0	0	1	

Values  
Should Be\*

PROPERTIES	SUS Viscosity @210°F	58.6	60-70	58.0	53.9	54.9	53.6
	cSt Viscosity @ 100°C	9.81	10.2-13.2	9.65	8.46	8.73	8.35
	Flashpoint in °F	435	>400	425	385	400	340
	Fuel %	<0.5	<2.0	<0.5	<0.5	<0.5	1.3
	Antifreeze %	0.0	0.0	0.0	0.0	0.0	0.0
	Water %	0.0	0.1	0.0	0.0	0.0	TR
	Insolubles %	0.2	<0.6	0.3	0.3	0.3	0.2
	TBN						
	TAN						
	ISO Code						

\*THIS COLUMN APPLIES ONLY TO THE CURRENT SAMPLE

This is Ryan's 1984 3/4-ton, flat-tappet Chevy engine. People have been talking for years about the lack of ZDDP in modern oil destroying flat-tappet engines, so Ryan decided to see what would happen if he ran an oil with no ZDDP in it whatsoever. He chose Aeroshell W65, which is close to a 10W/30 in viscosity. It was in place two and a half years and the engine is still running fine. Hmm...